

## **SECTION 306 DUST PALLIATIVE**

### **306.04      PREPARATION AND APPLICATION:**

- a.    Emulsified Asphalt - Revise the last sentence to read:

Apply the mixture according to Subsection 409.08 using the rate of 0.30 to 0.40 gallon per square yard.

Add the following paragraph to this item:

When required, loosen hard spots to a depth of ½ to 1 inch to allow fluid to penetrate where applied. Avoid puddles by blading and shaping uneven surfaces.

**END OF SECTION 306**

***END OF DIVISION 300***