

SECTION 306 DUST PALLIATIVE

306.04 PREPARATION AND APPLICATION:

- a. Emulsified Asphalt - Revise the last sentence to read:

Apply the mixture according to Subsection 409.08 using the rate of 0.30 to 0.40 gallon per square yard.

Add the following paragraph to this item:

When required, loosen hard spots to a depth of ½ to 1 inch to allow fluid to penetrate where applied. Avoid puddles by blading and shaping uneven surfaces.

END OF SECTION 306

END OF DIVISION 300